# **Royal El Minya White Cement**

# **CEM I 52.5 R**

Royal El Minya White Portland Cement, classified as CEM I 52.5 R according to EN 197-1:2011with CE Mark (0906-CBR 20000240011587), is a high-performance binder used in the production of white or colored masonry mortars, plasters, and concrete. Its superior whiteness, durability, and strength make it ideal for a wide range of architectural and structural applications.

## **Advantages**

- Superior quality High compressive strength ensures long-lasting structures
- Suitable for structural and aesthetic applications
- Enhances color vibrancy Works well with pigments for customized colors
- Provides excellent resistance to harsh environments
- Easy to mix and apply, enhancing construction efficiency

## **Applications**

- Architectural & Decorative Concrete Used in prestige buildings, façades, and white concrete structures.
- Precast Concrete Products Perfect for tiles, blocks, panels, and paving stones.
- Colored Concrete & Flooring Blends seamlessly with pigments for customized designs.
- Plasters & Dry Mixes Essential for smooth and aesthetically appealing finishes.
- Tile Adhesives & Grouts Ensures strong bonding and uniform appearance.
- Landscaping & Urban Design Used for garden elements, fountains, and walkways.
- Industrial & Infrastructure Projects Applied in bridges, tunnels, and high-end construction.

# **Cement Composition**

- Portland cement clinker 95 to 100 %
  - Minor additional constituents 0 to 5 %
- Regulatory Compliance:

White Portland CEM I 52.5 R-to EN 197-1:2011 standard (Portland cement, Hydraulic Cement

#### **Storage Conditions**

O Storage:

Recommended to retest after 6 weeks from the packing date if stored for long durations.

O Shelf Life:

Store in **dry, moisture-free conditions** to maintain product integrity.



# **Chemical, Physical & Mechanical Properties**

Parameter	Royal	Unit	Standard
Insoluble Residue %	1.0 ± 0.5	%	≤ 5
Ignition Loss (%)	3.8 ± 0.5	%	≤ 5
SO <sup>3</sup> (%)	3.5 ± 0.3	%	≤ 4
Chlorine (%)	0.05 ± 0.02	%	≤ 0.1
Hexavalent Chromium	≤ 0.6	ppm	≤ 2.0
Whiteness	≥ 85.5	%	
Initial Setting (min.)	90 ± 10	min	≥ 45
Soundness - (expansion)	1.0 ± 0.5	mm	≤ 10
2 Days Compressive Strength (N/mm²)	≥ 39 ± 2	N/mm²	≥ 30
28 Days Compressive Strength (N/mm²)	≥ 65.0 ± 3	N/mm²	≥ 52.5

## **Packaging & Shipping Options**

- Bulk Transport:
  - Shipped in vessels and containers for global export.
- Bagged Cement:
  - Available in 25 kg, 40 kg, and 50 kg bags.
  - Material options: P.P, C.P3L+PE, and C.P 3L+PE.
  - Securely packed on pallets.
  - Customization is available to meet specific customer requirements.
- O Big Bags (Jumbo Bags):
  - Customized as per customer request, with or without pallets, ensuring flexible packaging and transport solutions.